



MARNOT® XL HARDCOAT CLEAR POLYCARBONATE

Marnot films are a complete line of functional hardcoats designed for graphic arts applications.

Features of Marnot XL 100%, 90%, 75%, 55%, 35% Gloss Polycarbonate include:

- Excellent abrasion and scratch resistance
- Outstanding for embossing and die cutting
- Excellent chemical resistance to common household cleaners and industrial solvents
- Secod surface printability with solvent and UV inks
- First surface printability with clear, matte and texture UV cure inks

Marnot XL Clear Polycarbonate is available in web width of 48" and in 7, 10, 15, 20 and 30 mil thickness. Custom roll widths and sheet sizes are available.

TYPICAL VALUES ‡

| Physical | Test Method | Value | Unit |
|--|------------------|------------|--------|
| Specific Gravity | ASTM D792 | 1.2 | g/cm3 |
| Area Factor (Yield Factor) | | 0.0433 | Lb/in3 |
| Clarity | TM 10.76 | 98 | % |
| Haze | TM 10.76 | < 0.6 | % |
| Light Transmission | TM 10.76 | 91 | % |
| Gloss Back painted Flat Black | TM 10.15 | 92 | GU |
| 60 Degrees | | | |
| Gloss Clear Over White Matte 60 degrees | TM 10.15 | 164 | GU |
| Mechanical | Test Method | Value | Unit |
| Abrasion Resistance | TM 10.13 | 8 | |
| Pencil Hardness | TM 10.97 | HB | |
| Tensile Strength at Yield | ASTM D882 | 8400 | psi |
| Break, MD | | 8800 | psi |
| Tear Strength at Initiation | ASTM D1004 | 640 | g/mil |
| Tear Strength at Propagation | ASTM D1922 | 30 | g/mil |
| Thermal | Test Method | Value | Unit |
| Glass Transition | | 153 | С |
| Shrinkage MD TD | 30 min at 120C | 0.1 0.1 | % |
| Heat Aging | 170 Hours at 82C | No change | , 3 |

[‡] These are typical values only and should not be confused with specification values. Specifications, tolerances And minimum values are available on request from your Tekra representative or from Tekra Corporation

.

POST UV CURING CHEMICAL RESISTANCE

| Chemical | One Hour | 4 hours | |
|----------------------------------|------------|--------------|--|
| | Surface | surface | |
| | Contact at | contact at | |
| | 23C | 23C | |
| Acetone | Pass | Pass | |
| Concentrated HCI | Pass | Fail | |
| MEK | Pass | Pass | |
| Toluene | Pass | Pass | |
| Methylene Chloride | Pass | Pass | |
| Isopropyl Alcohol | Pass | Pass | |
| Cyclehexanone | Pass | Pass | |
| Ethyl Acetate | Pass | Pass | |
| Xylene | Pass | Pass | |
| Brake Fluid | Pass | Pass | |
| Butyl Cellosolve | Pass | Pass | |
| Hexane | Pass | Pass | |
| | | | |
| | 24 Hours | 24 hours | |
| | Surface | surface | |
| | Contact at | contact at | |
| | 23C | 50C | |
| Coffee | Pass | Slight Stain | |
| Fantastik ¹ | Pass | Pass | |
| Formula 409 ² | Pass | Pass | |
| Windex w/ Ammonia D ¹ | Pass | Pass | |
| Tide ³ | Pass | Pass | |
| Downy ³ | Pass | Pass | |
| 20% Bleach | Pass | Pass | |
| Mustard | Pass | Stain | |
| Mr. Clean ³ | Pass | Pass | |
| Ketchup | Pass | Pass | |
| Tea | Pass | Slight Stain | |
| Tomato Juice | Pass | Pass | |
| Lemon Juice | Pass | Pass | |
| Grape Juice | Pass | Slight Stain | |
| Vinegar | Pass | Pass | |
| Milk | Pass | Pass | |
| Armor All [†] | Pass | Pass | |
| Ethanol | Pass | Pass | |
| Salt Water | Pass | Pass | |
| Sunscreen | Pass | Pass | |
| Carlooroon | 1 400 | 1 400 | |

MASKING AND INTERLEAVING

Marnot XL Clear PC can be configured with mask on the second surface, or with mask on the first and second surfaces. If no protective masking is selected, Tekra will not warranty against spot abrasions or other damage to the uncoated surface in transit.

.

PROCESSABILITY

Tekra has made a good faith effort to validate the suitability of this product with common processing methods including screen printing, laser cutting, die cutting and embossing. However, because of the variability between different types of equipment, methods and processing conditions Tekra recommends that you work with your Tekra representative, your ink representative and your machine manufacturer to determine the substrates, inks, machinery and settings that work best in your particular situation.

The application suggestions, specifications and other data described here are based on experience that is believed by Tekra Corporation to be reliable. Because of the characteristics of these products, you should, before using these products in production, perform your own tests to determine to your satisfaction whether these products are acceptable and suitable for your particular purposes under your operation conditions.

Any order for these products will be subject to Tekra's terms and conditions of sale.

Version 1.5 - October 2016



TEKRA CORPORATION 16700 W LINCOLN AVE NEW BERLIN, WI 53151 800-448-3572



MARKING SYSTEMS 2601 MARKET STREET GARLAND, TX 75041 972-475-0770

¹ Registered Trademark of SC Johnson

² Registered Trademark of the Clorox Company

³ Registered Trademark of Proctor and Gamble

[†] Registered Trademark of ArmorAll Products Corp.