



Rigid Vinyl Press Polished – Polish/Polish

PROPERTY	TEST METHOD	TYPICAL VALUES
Specific Gravity	D-792	1.35 +/-0.01
Heat Deflection Temp (F deg @264psi annealed)	D-648	140 F +/- 4
Cold Break Temperature - C	D-1790	-20 C
Tensile Strength at Yield	D-882	6550 lb./sq in. +/-650
Elongation (at break)	D-882	180% +/-20
Tensile Impact Strength	D-53488	275 ft. lb/sq. in. +/-40